

USE OF INDUSTRIAL WASTE IN HIGHWAY CONSTRUCTION

Ankita Rawat¹, Abhishek², Sumit³, Razak Ansari⁴, Anuj Kumar Sharma⁵

1,2,3,4 B. Tech Student, Dept. of Civil Engineering, Greater Noida Institute of Technology, UP, India.
5 Assistant Professor, Dept. of Civil Engineering, Greater Noida Institute of Technology, UP, India.

Abstract— In present time, decomposition of industrial waste is a huge problem in India. A large quantity of waste material is dumped at land filling site, which if investigated properly can be utilized in highway construction and can reduce pollution. Different industrial products generate different waste material which is used for various purposes like fly ash used in concrete admixture, C&D waste used as base/sub-base material in coarse aggregates, silica fume used in PCC, etc. A new technique is being used for partially replacing the aggregates, sand, cement, soil, bitumen, etc. with industrial waste such rubber tyre used as admixture, marble dust as a filler in bituminous mix

Keywords— *Industrial waste, CBR test, fly ash, silica fume*

INTRODUCTION

India is a developing country where industrialization is growing very fast. With this, many problems also arise such as air pollution, disposal issue, landfilling. Some of the waste materials being a non-biodegradable become hazardous for the environment. India alone generating 4.43 million tons of hazardous wastes every year and it keeps on increasing. Many developing countries are using industrial waste materials to reduce the usage of natural resources and going towards the sustainable development where we can save the resources for our future generation. This is also cutting down the cost of extraction.

Industrial waste materials are like fly ash, silica fume, marble dust, cement kiln dust, waste tyres, glass waste, china clay, etc. We got these waste materials from different industries. Since ages we are using aggregates, soil, sand, cement, bitumen, etc for road construction but as natural resources being inadequate in nature we are looking for an alternative of these materials. Many researchers are experimenting on different waste materials which can fulfil the properties of aggregates, soil, sand, bitumen, cement, etc. Materials like fly ash from thermal power plant, marble dust from marble industry, waste tyre from rubber industry, red mud from alumina industry, silica fume from silicon industry, and construction and demolition waste from construction industry, etc have being proved to be useful and alternative for natural resources in many countries.

LITERATURE REVIEW

- Anurag K. Gahalod, Vikas Bankar and Payal Nit, Department of civil engineering, Maharashtra, India**
 - Construction and demolition (C&D) waste and tiles waste materials were studied.

- They worked on how to use C&D waste and tiles waste as an alternative to aggregates.
- It was found that it is possible to replace 50% of aggregates with C&D waste and tiles waste.

- Sheeraz Ahmad Khan and Saurabh Gupta, Department of Civil Engineering, Kathgarh, India**

- Waste foundry sand (WFS) and fly ash used, as an industrial waste, which was collected from local industry and then their physical and chemical properties were analyzed.
- They took different proportion of WFS and fly ash together and did some test like CBR (California bearing ratio) test, Split tensile test, and permeability test.
- They found that 70% of WFS increases the CBR value. by increasing the fly ash percentage, split tensile strength of the material also increases the.

- Tara Sen and Umesh Mishra, Department of Civil Engineering, Agartala, India**

- Different types of industrial waste such as fly ash, blast furnace slag, cement kiln dust, phosphogypsum, waste plastic bags, foundry sand and colliery sand studied.
- They studied previous research paper and analyzed that these materials are enhancing the performance of concrete by being the alternatives of concrete aggregates or alternate binder to cement or as a filler material.

- Rokade S, Department of Civil Engineering, Bhopal, India**

- He studied the plastic waste and rubber tyres waste. He experimented the semi dense bituminous concrete (SDBC) mix by using Marshall Method of bituminous mix design.
- The SDBC was prepared with conventional 60/70 grade bitumen added with varying percentage of low-density polyethylene (LDPE) and crumb rubber (CRMB).
- The result shows that the Marshall Stability value, which is the strength parameter of SDBC, increased by 25% by addition of LDPE and CRMB. the density of the mix also increased in both the cases.

MATERIAL

Fly ash was collected from local industry. Its physical and chemical properties were analysed. The shape of fly ash particles are spherical and it increases the flow ability, which

reduces the amount of water required for the mixture. Silica fume contains more than 90 percent of silicon dioxide.

EXPERIMENT

In this experimental study we have taken total of 17 samples. The total amount of industrial waste that is fly ash and silica fume is taken 90 percent with different proportions of fly ash and silica fume which is added with 10 percent of stabilizing material like cement and lime. The proportions of 17 samples are as given in following table.

Table 1: Mixture ratio measured for CBR test

S.No.	Waste material		Stabilized Product		CBR
	Fly Ash	Silica Fume	Cement	Lime	
1	45	45	05	05	32
2	50	40	00	10	38
3	55	35	05	05	50
4	60	30	10	00	70
5	65	25	05	05	80
6	70	20	00	10	82
7	75	15	05	05	85
8	80	10	10	00	71
9	85	5	05	05	59
10	40	50	00	10	47
11	35	55	05	05	40
12	30	60	10	00	42
13	25	65	05	05	37
14	20	70	00	10	35
15	15	75	05	05	30
16	10	80	10	00	50
17	5	85	5	5	55

RESULT

California Bearing Ratio Test

This method is used for evaluating the strength of subgrade soil and other pavement materials for the design and construction. The basic principle in CBR test is causing a cylindrical plunger of 50 mm diameter to penetrate the soil or pavement component material to be tested at a rate of 1.25 mm per minute.

Table 2: Result of CBR Test

S.No.	Waste material		Stabilized Product		CBR
	Fly Ash	Silica Fume	Cement	Lime	
1	45	45	5	5	32
2	50	40	0	10	38
3	55	35	5	5	50
4	60	30	10	0	70
5	65	25	5	5	80
6	70	20	0	10	82
7	75	15	5	5	85
8	80	10	10	0	71
9	85	5	5	5	59
10	40	50	0	10	47
11	35	55	5	5	40
12	30	60	10	0	42
13	25	65	5	5	37
14	20	70	0	10	35
15	15	75	5	5	30
16	10	80	10	0	50
17	5	85	5	5	55

The optimal value of CBR test is found to be more with 75 percent of fly ash and 15 percent of silica fume which resulted in higher CBR value. It is possible due to the following factors because the mixture worked as a concrete mix and fly ash increases the strength and workability of cement by greater measures means fly ash may be worked as a coarse aggregate and for silica fume addition refines pore structure and produces concrete of improved mechanical strength.

CONCLUSION

After experimenting on these materials with found out that:

- When fly ash was 75%, it found that it has more effective in giving CBR value.
- The value of CBR reduced by 15% when silica fume was used in the mixture.
- The change in CBR values related to the proportion of fly ash used in the mixture is generally not linear.

REFERENCE

- [1] [Book] Chunhua Han and Ann M. Johnson, "waste products in highway construction", braun intrtec corporation, pp.- 62-69, 1993.
- [2] Abdel-rahman megahid, hassan younis, talaat abdel-wahed, eman abdel-sabour, "utilization of industrial waste material in highway construction", jes, journal of engineering science, vol. 48, no. 3, may 2020.
- [3] K Aravind, Animesh Das, "Industrial waste in highway construction", iitd.ac.in, 2007.
- [4] Tara Sen and Umesh Mishra, "Usage of industrial waste products in village road construction", International Journal of Environmental Science and Development, Vol. 1, No. 2, ISSN: 2010-0264, June 2010.
- [5] Md. Shah Azam, Rachana Verma, Anuj Kumar Sharma, Mukesh Kumar, "Construction of Highway Using Industrial Waste", International Research Journal of Engineering and Technology (IRJET), Vol. 07, Issue 07, July 2020.
- [6] Sheeraz Ahmad Khan, Saurabh Gupta, "Analysis on Highway Construction Made From Industrial Waste and It's By-product",

International Journal of Research in Engineering, Science and Management, Vol. 04, Issue 10, October 2021.

- [7] Chandravali Pandey, Dr. Shubha Agarwal, "Comparative Study Between Soaked and Unsoaked Value of Soil Samples", International Research Journal of Engineering and Technology(IRJET), Volume: 06, Issue: 06, June 2019